



# TEXAS CRUSHED STONE COMPANY

P.O. Box 1000 · Georgetown, Texas 78627-1000 · Phone 512/930-0106 · Austin 512/255-4405 · Fax 512/244-6055 · [txcrushstone@msn.com](mailto:txcrushstone@msn.com)

## ASTM SAND TCS # 573

### SPECIFICATIONS:

<u>SIEVE SIZE</u>	<u>% RETAINED</u>	<u>TCS AVG. SAMPLE</u>	<u>TCS LOW</u>	<u>TCS HIGH</u>
4m	0-5	T	T	T
8m	5-20	6.0	4.0	18.0
16m	15-50	37.0	20.0	48.0
30m	40-75	57.0	50.0	69.0
50m	70-90	73.0	75.0	85.0
100m	90-100	90.5	90.0	95.0